



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : D06N 3/00, 7/00, A61L 15/00, A61F 13/00	A1	(11) International Publication Number: WO 00/65143 (43) International Publication Date: 2 November 2000 (02.11.00)
(21) International Application Number: PCT/GB00/01415 (22) International Filing Date: 13 April 2000 (13.04.00) (30) Priority Data: 9909349.4 23 April 1999 (23.04.99) GB (71) Applicant (for all designated States except US): FIRST WATER LIMITED [GB/GB]; Hilldrop Lane, Ramsbury, Marlborough, Wiltshire SN8 2RB (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): MUNRO, Hugh, Semple [GB/GB]; Barton Cottage, Weston Sub Edge, Chipping Camden, Warwickshire GL55 6QT (GB). LAWRENCE, Steven, John [GB/GB]; 67 Keresley Road, Coventry CV6 2JB (GB). (74) Agent: BROWN, David, Leslie; Page Hargrave, Southgate, Whitefriars, Lewins Mead, Bristol BS1 2NT (GB).		(81) Designated States: AE, AG, AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), DM, DZ, EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KR (Utility model), KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: PROCESS FOR COATING A PERFORATED SUBSTRATE (57) Abstract <p>A process for coating a perforated substrate with a gel (e.g. a polymerised acrylate hydrogel or a xerogel) without substantial occlusion of the perforations comprises (i) forming a layer of a liquid pregel mixture, comprising one or more monomers, on a web coated with a silicone, polyethylene, Teflon (R) or other coating having a surface energy less than the surface energy of the liquid pregel mixture; (ii) contacting the perforated substrate with the liquid pregel mixture; and (iii) curing the liquid pregel mixture. Preferably at least part of the curing takes place while the liquid pregel mixture is in contact with both the perforated substrate and the web. The process is especially applicable to the manufacture of attachment tabs for wigs and toupees, wound dressings, patches for transdermal drug delivery, therapeutic patches or biomedical skin electrodes.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

PROCESS FOR COATING A PERFORATED SUBSTRATE

5 This invention relates to a process for coating a perforated substrate with a gel and to coated perforated substrates obtainable by the process.

Background

10 Gel coated perforated substrates are known for use in a variety of consumer care applications, for example as wound dressings. The problem with existing methods for their preparation is that it is difficult to ensure that the perforations in the substrate are not occluded by the gel.

15 Furthermore known processes (see for example that used in US 5352508 (Cheong) to produce a wound dressing) encapsulate the perforated substrate within the gel. This is a problem because both sides of the substrate encapsulated by the gel are tacky and will need protecting with additional layers which adds complication and cost to the production process. In use it can be disadvantageous to have gel on both sides of the substrate. For example where the encapsulated substrate is to be used as a wound dressing which contacts the wound directly, it is not possible to have removable surface dressings (e.g. to absorb the exudate from the wound) on top of the wound dressing. 20 This is because when the surface dressings are removed, they will disturb the wound dressing itself which potentially would interfere with the healing process.

25 It is an object of this invention to provide an improved process for coating a perforated substrate with a gel whereby substantially all of the perforations of the coated substrate produced are not occluded and wherein preferably only one side of the substrate is coated by the gel.

Summary of the Invention

30 According to the present invention there is provided a process for coating a perforated substrate with a gel without substantial occlusion of the perforations, which process comprises:

-2-

- (i) forming (e.g. by extrusion) a layer of a liquid pregel mixture, comprising one or more monomers, on a web coated with a coating having a surface energy less than the surface energy of the liquid pregel mixture;
- 5 (ii) contacting the perforated substrate with the liquid pregel mixture layer ; and
- (iii) curing the liquid pregel mixture.
- 10

The web is preferably removed after at least an initial partial curing of step (iii).

15 According to the present invention there is further provided a coated perforated substrate obtainable by the process of the invention, which substrate is coated with a gel.

20 The term "perforated substrate" used herein refers to any substrate (including a portion thereof) having perforations (foramina). In particular, it includes woven and non-woven mesh fabrics. Further details of suitable perforated substrates are given below.

25 The term "without substantial occlusion of the perforations" used herein refers to at least about 70%, typically at least about 80%, more preferably at least about 90%, most preferably at least about 95%, of the perforations in the substrate being unoccluded.

30 In a particularly preferred embodiment, the invention provides a process for coating with a gel at least a portion of at least one major face of a planar perforated substrate having first and second major faces, and at least partially coated perforated substrates prepared thereby.

The web used in the invention is generally coated with any coating generally known in the art to reduce the surface energy of the material to which it is applied. For example a suitable coating is silicone, polyethylene, polyvinyl fluoride or polytetrafluoroethylene (PTFE) (for example that sold under the trade name Teflon). The web is preferably made from paper, polyester, polyolefin or any other material that can act as a support for a low energy surface coating.

The coated perforated substrate according to the invention is useful in a wide variety of applications, including consumer care applications especially where the permeability or breathability of the perforated substrate is useful such as for cosmetic applications, e.g. for the attachment of wigs or toupees, or for therapeutic applications, e.g. as wound dressings, transdermal drug delivery, therapeutic patches or as electrodes (e.g. biomedical skin electrodes).

One advantage of the process according to the invention is that the perforations of the coated perforated substrate produced by the process are substantially unoccluded by gel. Without restricting the scope of the invention claimed, it is believed to be due to the combination of the contraction of the pregel after extrusion and the low surface energy of the web. This is because of the difference in surface energy between the pregel and the web as the pregel has a higher surface energy. The gel does not contract immediately because it is generally extruded in a relatively large amount. Thus it is not until the perforated substrate is applied on top of the extruded pregel that the pregel reticulates such that the perforations start to become free from the pregel.

The amount of the pregel extruded is generally from 0.01kg/m^2 to 3kg/m^2 . The amount used will depend upon the intended purpose of the coated substrate. In general the amount should not be so small that the reticulation of the pregel on the substrate leads to the pregel becoming discontinuous with the formation of unconnected "islands" of pregel on the substrate. On the other hand the amount of pregel should not be so much that reticulation cannot occur. The coating weight of pregel at which these limitations are reached will depend upon a variety of factors including the viscosity of the pregel, the surface energy of the pregel and of the coating on the web, the size and number of the perforations in the substrate and the nature of the substrate itself.

The substrate/pregel/web assembly is then subjected to an initial cure which is found to further encourage the non-occlusion of the perforations. The web is then removed from the coated substrate. Optionally a final cure is applied, if necessary,
5 either before or after the web is removed from the coated substrate. Conventional means are used to cure the gel e.g. heat, irradiation by UV light or electron beams.

A release sheet is optionally applied to the (or each) coated face of the substrate to support and protect it. The release sheet is generally either made of plastic
10 or coated paper e.g. siliconised paper.

The perforated substrate used in the invention is generally any conventional substrate. The substrate is typically planar having first and second major faces, one (or, less preferably, both) of which is/are to be gel-coated. The substrate is generally either
15 knitted, extruded, woven or non-woven. The smallest dimension of each perforation in the substrate is preferably from 0.5 to 5.0mm, more preferably from 1.0 to 3.0mm. The fibres are made from, for example, cotton, rayon, polyester, polyamide, polypropylene, polyamide and/or wool. The substrate, in the case of a patch for transdermal (iontophoretic) drug delivery or a biomedical skin electrode, may be electrically
20 conductive.

It is found that the method of the present invention enables at least one major face of the perforated substrate to be satisfactorily coated with gel, without substantial occlusion of the perforation.
25

Generally the gel formed by the liquid pregel mixture used in the invention is any gel conventionally used to coat substrates, for example, to act as an adhesive. Preferably the gel formed by the pregel is a tacky gel such as a hydrogel or a xerogel. The gel is preferably a skin-compatible tacky hydrogel. Typically the pregel mixture
30 used to form a hydrogel is an aqueous solution of one or more ionic monomers, optionally in association with a cross-linking agent.

In preferred embodiments the one or more ionic monomers will be acrylate based monomers selected for their ability to polymerise rapidly in water. Where there is more than one monomer, they preferably have substantially the same molecular weight whereby in a mixture of the two the relative proportions may be varied without significantly altering the molar characteristics of the composition. The one or more ionic monomers are preferably included in the composition in an amount by weight of from 1% to 95%, more preferably from 10% to 70%, most preferably from 15% to 60%.

Preferably the one or more ionic monomers are 2-acrylamido-2-methylpropane sulphonic acid or an analogue thereof or one of its salts, e.g. an alkaline metal salt such as a sodium, potassium or lithium salts; acrylic acid or an analogue thereof or one of its salts, e.g. an alkaline metal salt such as a sodium, potassium or lithium salt; and/or a polymerisable sulphonate or a salt e.g. an alkaline metal salt such as a sodium, potassium or lithium salt, of acrylic acid (3-sulphopropyl)ester or an analogue thereof. The term "analogue" in this context refers particularly to substituted derivatives of 2-acrylamido-2-methylpropane sulphonic acid, of acrylic acid or of acrylic acid (3-sulphopropyl) ester.

A particularly preferred ionic monomer is a sodium salt of 2-acrylamido-2-methylpropane sulphonic acid, commonly known as NaAMPS which is available commercially at present from Lubrizol as either a 50% aqueous solution (reference code LZ2405) or a 58% aqueous solution (reference code LZ2405A) and/or acrylic acid (3-sulphopropyl) ester potassium salt, commonly known as SPA. SPA is available commercially in the form of a pure solid from Raschig.

Conventional crosslinking agents are preferably used to provide the necessary mechanical stability and to control the adhesive properties of the hydrogel. Preferably a crosslinker is included in an amount of at least 0.05% by weight. Typical crosslinkers include tripropylene glycol diacrylate, ethylene glycol dimethacrylate, triacrylate, polyethylene glycol diacrylate (PEG400 or PEG600), methylene bis acrylamide.

It has also been found that the addition of a polyhydric alcohol (such as glycerol, sorbitol or polyethylene glycol) to the pregel enhances the solubilisation

process. This pregel is then converted into a gel by a free radical polymerisation reaction. This may be achieved for example using conventional thermal initiators and/or photoinitiators or by ionizing radiation. Photoinitiation is a preferred method and will usually be applied by subjecting the pre-gel reaction mixture containing an appropriate photoinitiation agent, for example Irgacure 184 (which is made by Ciba), to UV light after it has been spread or coated as a layer on siliconised release paper or other solid substrate. The processing will generally be carried out in a controlled manner involving a precise predetermined sequence of mixing and thermal treatment or history.

Features or characteristics of importance include the adhesive properties of the hydrogel which depend not only on the nature of the monomers used to form the hydrogel but also on the manner of processing, nature of plasticiser used and of added electrolyte (if any). These features, as well as the possible use of interpenetrants and other additives are discussed below.

Adhesion

The performance of hydrogels as pressure sensitive adhesives is related to the surface energetics of the adhesive and of the adherend (for example mammalian skin) and to the viscoelastic response of the bulk adhesive. The requirement that the adhesive wet the adherend to maximise the work of adhesion is well known. This requirement is generally met when the adhesive has a similar or lower surface energy to the adherend. The viscoelastic properties, in particular the elastic or storage modulus (G') as measured by dynamic mechanical testing at low frequency (approximately 0.01 to 1Hz) and high frequency (100 to 1000Hz) have been related to the wetting/creep behaviour and peel/quick stick properties respectively. The choice, assembly and processing of the ingredients of the hydrogel adhesive is usually targetted at making a material with a balance of properties suitable for pressure sensitive adhesive applications. We have found that hydrogels with suitable surface energetics (for example 20 to 50 dynes/cm) will function as useful adhesives capable of subsequent conversion into a product if the elastic moduli are within the ranges 500 to 20,000 Pa at a frequency of ca 1Hz, temperature 20° to 40° Celsius and 1000 to 100,000 Pa at a frequency of 100 Hz. A balance between the quantities and nature of polymer, plasticiser and the degree of crosslinking/entanglement has to be achieved.

Plasticiser

The pregel for use in producing a hydrogel generally comprises, in addition to one or more ionic monomers, an aqueous plasticising medium and, optionally, additional electrolyte. It has been found that the activity of the water together with the rheological properties of the hydrogels generally need to be controlled to produce optimum pressure sensitive adhesive properties. One preferred feature of the preferred pregel used in the invention to form a hydrogel is that to achieve the desired adhesive properties the final amount of water required in the hydrogel is present in the pregel prior to gellation, i.e. no water is added to or removed from the hydrogel after manufacture. The pregel preferably comprises from 3% to 40% of water by weight of the mixture. The water acts both as a solvent for the monomers and as a plasticiser.

The aqueous plasticising medium optionally additionally comprises a polymeric or non-polymeric polyhydric alcohol (such as glycerol), an ester derived therefrom and/or a polymeric alcohol (such as polyethylene oxide). Glycerol is the preferred plasticiser. An alternative preferred plasticiser is an ester derived from boric acid and a polyhydric alcohol (such as glycerol). The pregel preferably comprises from 10% to 50%, preferably from 10% to 45%, of plasticiser (other than water) by weight of the mixture.

Plasticisers are generally used in the invention to control adhesive properties. Whilst the presence of glycerol or other polyhydric alcohols in other reported formulations has been quoted to provide humectant properties to the hydrogel, it has been discovered that the most important parameter to preventing water loss is the activity of the water within the hydrogel which in turn depends on the nature and proportions of the other components and manner of processing. The water activity of the hydrogel can be measured using impedance methods with devices such as the Rotronic AWVC (manufactured by Rotronic). The activity of water may also be determined by placing the hydrogel in environments of controlled humidity and temperature and measuring the changes in weight. The relative humidity (RH) at which the hydrogel does not change weight corresponds to the activity of water in the gel (%RH/100). The use of saturated salt solutions to provide the appropriate environmental conditions is well known. All hydrogels directly exposed to relative

humidities less than that corresponding to the activity of water will be thermodynamically allowed to lose water. Exposure to greater relative humidities and the gel will gain weight. Water activity in the hydrogel is primarily dependent on the water content and the nature of the polymeric components and the way in which they are processed. Water activity has been shown to have a better correlation with the growth of bacteria and moulds than water content. It has been found that organisms struggle to grow at water activities less than 0.8. Enzyme activity has also been reported to decrease significantly below activity of 0.8.

One advantage of using hydrogels is that when they have water activities from 0.4 to 0.85, preferably from 0.65 to 0.8 and more preferably from 0.7 to 0.8, they are adhesive to dry skin. This is because they have a greater tendency to wet (i.e. donate water to the skin) rather than to extract. These materials do not encourage the growth of microbial agents and they can be sterilised. Hydrogels based on the curing of ionic monomers are preferred as they enable a greater control of the activity of water. For materials with requirements for higher water activities, e.g. from 0.75 to 0.85, monomers which are potassium salts are preferred, e.g. SPA, K AMPS, and K acrylate.

Interpenetrants

Hydrogels based on interpenetrating polymer networks (IPN) are well known. As IPN has been defined as a combination of two polymers, each in network form, at least one of which has been synthesised and/or crosslinked in the presence of the other. As will be appreciated, this combination will generally be a physical combination rather than a chemical combination of the two polymers. IPN systems may be described by way of example as follows:

Monomer 1 is polymerised and crosslinked to give a polymer which is then swollen with monomer 2 plus its own crosslinker and initiator.

If only one polymer in the system is crosslinked the network formed is called a semi-IPN. Although they are also known as IPN's, it is only if there is total mutual solubility that full interpenetration occurs. In most IPN's there is, therefore, some phase separation but this may be reduced by chain entanglement between the polymers. It has

also been reported that semi IPN's can be made in the presence of carrier solvents (for example water in the case of hydrophilic components).

5 It has been found that polymerising and crosslinking water soluble monomers in the presence of water soluble polymers, water and polyhydric alcohols produces hydrogel materials with enhanced rheological and consequently adhesive properties.

Suitable water soluble polymers for the formation of semi IPN's include poly (2-acrylamido-2-methylpropane sulphonic acid) or one of its salts and its copolymers, 10 poly (acrylic acid-(3-sulphopropyl) ester potassium salt), copolymers of NaAMPS and SPA, polyacrylic acid, polymethacrylic acid, polyethylene oxide, polyvinyl methyl ether, polyvinyl alcohol, polyvinylpyrrolidone, its copolymers with vinyl acetate, dimethylaminoethyl methacrylate, terpolymers with dimethylaminoethyl methacrylate and vinylcaprolactam, polysaccharides such as gum arabic, karaya gum, xanthan gum, 15 guar gum, carboxymethyl cellulose (CMC), NaCMC, hydroxypropylmethyl cellulose (HPMC), hydroxyethyl cellulose (HEC) or combinations thereof.

The amount of interpenetrant polymer used will be dependent on the mechanical and rheological properties required as well on consideration of processing 20 conditions. If the interpenetrant polymer used increases the viscosity of the pre-gel mix beyond 5000 centipoise we have found that the monomers do not polymerise and crosslink on an acceptable time scale (should be less than 60 seconds, preferably less than 10 seconds). The viscosity depends on the nature and molecular weight of the interpenetrant and the nature of pre-gel processing.

25

Of the natural polysaccharides, gum arabic is usually preferred due to its cold water solubility and lesser effect on viscosity compared with, for example, karaya gum. A higher concentration of gum arabic than karaya may therefore be used if desired, enabling a wider control of hydrogel properties. It has also been found that the 30 processing steps for assembling the pre-gel formulation can be critical with respect to the properties of the manufactured hydrogel. For a given formulation, if the components are assembled at 25°C and cured different adhesive properties are obtained compared to those that have been heated to 70°C. Solutions containing natural polysaccharides

become less opaque indicative of improved solubility. The activity of water in hydrogels prepared from heat treated pre-gels generally is lower than in non heat treated pre-gels.

5 Other additives

Non-hydrophilic polymers may also be incorporated either in the presence or absence of interpenetrant polymers to form phase separated materials. The preparation of two phase composites consisting of a hydrophilic polymer containing an ionically conducting continuous phase and domains of a hydrophobic pressure sensitive adhesive
10 which enhance adhesion to mammalian skin have been reported in U.S. Patent 5338490. The method of preparation described therein involved casting a mixture (as a solution and or suspension) consisting of the hydrophilic polymer containing phase and hydrophobic components onto a substrate and then removing the solvent. It has been found, however, that adhesive ionically conducting hydrogels may be better prepared
15 by combining the hydrophobic polymer (preferably as an emulsion) with the components of the pre-gel reaction mixture and casting these onto a substrate and curing. In other words, there is no need to remove a solvent in order to form useful materials. Furthermore, the hydrophilic phase in addition to being a crosslinked network may also be an IPN or semi IPN.

20

It is believed that when hydrophobic polymers are incorporated in this way that the hydrophobic component segregates to the surface (as determined by Fourier transform infrared attenuated total reflectance spectroscopy, FTIR ATR, approximate sampling depth 0.5microns) and that it is the amount of the hydrophobic component
25 present in the surface that influences the adhesion to a wide variety of materials. The greater the amount of the hydrophobic component the greater the adhesion. In U.S. Patent 5338490 weight ratios of the hydrophilic phase to the hydrophobic phase of 60:1 to 8:1 were claimed. In hydrogel adhesives of between 100 to 2000 microns thick made in accordance with the present invention, ratios of hydrophilic to hydrophobic
30 components ranging from 7:1 to 1:50 have been found to be preferable, especially when these ratios are present in the surface of the adhesive composition. In the process of the present invention, however, it may take up to 72 hours from the initial curing of the

adhesive hydrogel for the segregation of the hydrophobic materials to the surface, as defined by the ATR sampling depth, to be complete.

5 Preferably, the hydrophobic pressure sensitive adhesive in such embodiments is selected from the group consisting of polyacrylates, polyolefins, silicone adhesives, natural or synthetically derived rubber base and polyvinyl ethers or blends thereof. Preferably the hydrophobic pressure sensitive adhesive in these embodiments is an ethylene/vinyl acetate copolymer such as that designated DM137 available from Harco or a vinyl acetate dioctyl maleate copolymer available from Air Products (sold under the trade name Flexbond 150). Those skilled in the art will also know that the molecular weight and comonomer ratios may be altered to control the properties of hydrophobic pressure sensitive adhesives. In general, the degree of surface segregation exhibited by such hydrophobic pressure sensitive adhesive (HPSA) will be dependent on factors such as composition of the HPSA, viscosity of the pre-gel mixture, temperature and rate of curing.

Additional functional ingredients may also incorporated in the pregels used in the invention, including antimicrobial agents (e.g. citric acid, stannous chloride) and, for drug delivery applications, pharmaceutically active agents, the latter being designed to be delivered either passively (e.g. transdermally) or actively (e.g. iontophoretically) through the skin.

The invention will be further described with reference to the following Example which should not be understood to limit the scope of the invention.

EXAMPLE 1

To 57 parts of a 58% solution of the sodium salt of 2-acrylamido-2-methylpropane sulphonic acid (NaAMPS) (LZ2405A) 10 parts of a 58% solution of the potassium salt of 3-sulphopropyl acrylate (SPA) were added along with 5 parts potassium chloride and stirred until the potassium chloride has dissolved. This solution was then mixed with 30 parts glycerol for 30 minutes. To the latter solution were added 0.15 parts of a solution containing 20 parts of polyethylene glycol diacrylate (pEG600)

-12-

(product of UCB Chemicals marketed under the trade name designation of Ebacryl 11) in which 6 parts of 1-hydroxycyclohexyl phenyl ketone (product of Ciba and marketed under the trade name designation of Irgacure 184) were dissolved. The so-formed pre-gel solution was then extruded through a 15cm (6 inch) width slot die onto a web of
5 siliconised paper (weight 140 g/m², supplied by Coatec) moving at a rate of 5 metres per minute at a coat weight of 0.8kg/m². A 100% polyester mesh (sold under the trade name BG3486 by Brightwater) was laid on top and the assembly was cured by being passed
10 under a medium pressure mercury arc lamp at a speed of 5 meters per minute. The residence time under the lamp was 4 seconds. On completion of curing and removal of
the web the polyester mesh was found to be gel-coated on only one of its major surfaces, with more than 70% of the perforations being unoccluded by gel.

As will be seen, the invention presents a number of different aspects and it should be understood that it embraces within its scope all novel and inventive features
15 and aspects herein disclosed, either explicitly or implicitly and either singly or in combination with one another. Also, many detail modifications are possible and, in particular, the scope of the invention is not to be construed as being limited by the illustrative example(s) or by the terms and expressions used herein merely in a
descriptive or explanatory sense.

20

CLAIMS

1. A process for coating a perforated substrate with a gel without substantial occlusion of the perforations, which process comprises:
- 5
- (i) forming a layer of a liquid pregel mixture, comprising one or more monomers, on a web coated with a coating having a surface energy less than the surface energy of the liquid pregel mixture;
 - (ii) contacting the perforated substrate with the liquid pregel mixture; and
 - 10 (iii) curing the liquid pregel mixture.
2. A process according to claim 1, wherein the layer of the liquid pregel mixture is formed by extrusion of the liquid pregel mixture onto the web.
- 15 3. A process according to claim 1 or claim 2, wherein the contacting of the perforated substrate with the liquid pregel mixture is achieved by applying the substrate to the pregel mixture on the web.
4. A process according to any one of the preceding claims, wherein the weight of liquid pregel mixture on the web is between about 0.01 to about 3 kg/m².
- 20
5. A process according to any one of the preceding claims, wherein at least some of the curing takes place while the liquid pregel mixture is in contact with both the perforated substrate and the web.
- 25
6. A process according to any one of the preceding claims, wherein at least some of the curing takes place while the liquid pregel mixture is in contact with the perforated substrate after removal of the web.
- 30 7. A process according to any one of the preceding claims, wherein the web comprises paper, polyester, polyolefin or any combination thereof.

8. A process according to any one of the preceding claims, wherein the coating of the web comprises silicone, polyethylene, polyvinyl fluoride, PTFE or any mixture or combination thereof.
- 5 9. A process according to any one of the preceding claims, wherein the perforated substrate is planar, having first and second major faces, and the process applies the gel to at least a portion of at least one major face of the substrate.
- 10 10. A process according to claim 9, wherein the planar perforated substrate comprises woven or non-woven fibres of cotton, rayon, polyester, polyamide, polypropylene, wool or any mixture or combination thereof.
- 15 11. A process according to any one of the preceding claims, wherein the one or more monomers comprise at least one acrylate based monomer.
12. A process according to any one of the preceding claims, wherein the liquid pregel mixture includes one or more crosslinking agents for the monomer(s).
- 20 13. A process according to any one of the preceding claims, wherein the liquid pregel mixture is an aqueous mixture, optionally including also at least one plasticising agent other than water.
- 25 14. A process according to claim 13, wherein the liquid pregel mixture includes from about 3% to about 40% by weight of water.
15. A process according to any one of the preceding claims, wherein the curing is performed by heat, ultra-violet irradiation, electron beam irradiation or any combination thereof.
- 30 16. A gel-coated, perforated substrate obtained by a process according to any one of the preceding claims.

- 5 17. A gel-coated, perforated substrate, wherein the substrate is coated with a cured gel formed by polymerisation of one or more monomers, optionally in the presence of one or more crosslinking agents for the monomer(s), the perforations of the substrate being substantially unoccluded by the gel and the coated substrate being obtainable by a process according to any one of claims 1 to 15.
- 10 18. A gel-coated, perforated substrate according to either of claims 16 and 17, wherein only one side of the substrate is coated by the gel.
- 15 19. A gel-coated, perforated substrate according to claim 18, wherein the gel coat is protected by a contacting release sheet.
20. An article comprising a gel-coated, perforated substrate according to any one of claims 16 to 19, the article being an attachment tab for a wig or toupee, a wound dressing, a patch for transdermal drug delivery, a therapeutic patch or a biomedical skin electrode.

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 D06N3/00 D06N7/00 A61L15/00 A61F13/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D06N A61L A61F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, PAJ, EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 93 19709 A (MOELNLYCKE AB ;FABO TOMAS (SE)) 14 October 1993 (1993-10-14)	16-18,20
Y	claims	1-15
X	US 4 921 704 A (FABO TOMAS) 1 May 1990 (1990-05-01) column 2, line 28 - line 59; claims; figures	16, 18, 20
X	US 4 838 253 A (BRASSINGTON NIGEL J ET AL) 13 June 1989 (1989-06-13)	16-18,20
A	column 4, line 38 -column 5, line 28; claims	1-15
	— -/-	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

3 August 2000

Date of mailing of the international search report

09/08/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Pamies Olle, S

INTERNATIONAL SEARCH REPORT

Internat'l Application No

PCT/GB 00/01415

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 352 508 A (CHEONG CATHERINE L) 4 October 1994 (1994-10-04) cited in the application column 3, paragraph 2 - paragraph 3; claims; examples	16-20
Y	column 4, line 11 -column 5, line 65	1-15
P,X	FR 2 783 412 A (LHD LAB HYGIENE DIETETIQUE) 24 March 2000 (2000-03-24)	16,17, 19,20
P,A	claims; example 1	1-15
Y	US 4 661 099 A (RUPP ROLAND ET AL) 28 April 1987 (1987-04-28) abstract; claims column 4, line 43 -column 5, line 32	1-10,15
Y	WO 97 42985 A (LINDQVIST BENGT W ;FABO THOMAS (SE); MOELNLYCKE AB (SE); ARESKOUG) 20 November 1997 (1997-11-20) page 4, line 4 -page 5, line 16; claims; figures page 9	1-10,15
Y	EP 0 676 457 A (GRAPHIC CONTROLS CORP) 11 October 1995 (1995-10-11) claims	11-14

INTERNATIONAL SEARCH REPORT

Information on patent family members

Internal Application No

PCT/GB 00/01415

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9319709	A	14-10-1993	SE 500972 C	10-10-1994
			DE 69311101 D	03-07-1997
			DE 69311101 T	18-09-1997
			EP 0633757 A	18-01-1995
			ES 2105241 T	16-10-1997
			JP 7505309 T	15-06-1995
			SE 9200983 A	01-10-1993
			US 5635201 A	03-06-1997
US 4921704	A	01-05-1990	SE 455466 B	18-07-1988
			AT 71274 T	15-01-1992
			CA 1329082 A	03-05-1994
			DE 3775868 A	20-02-1992
			DK 583387 A	06-11-1987
			EP 0261167 A	30-03-1988
			FI 874635 A, B,	21-10-1987
			JP 2525215 B	14-08-1996
			JP 63502804 T	20-10-1988
			NO 874545 A, B,	02-11-1987
			SE 8601098 A	11-09-1987
			WO 8705206 A	11-09-1987
			US 5340363 A	23-08-1994
US 4838253	A	13-06-1989	GB 2192142 A	06-01-1988
			AU 604714 B	03-01-1991
			AU 7506687 A	07-01-1988
			BR 8703398 A	22-03-1988
			CA 1320085 A	13-07-1993
			DE 3782095 A	12-11-1992
			DE 3782095 T	13-05-1993
			EP 0251810 A	07-01-1988
			GB 2226780 A, B	11-07-1990
			HK 72692 A	02-10-1992
			IE 61933 B	30-11-1994
			MX 168354 B	19-05-1993
			NZ 220884 A	27-10-1989
			SG 80392 G	02-10-1992
			ZA 8704858 A	22-02-1989
US 5352508	A	04-10-1994	AT 145541 T	15-12-1996
			AU 646541 B	24-02-1994
			AU 1052692 A	06-08-1992
			BR 9200312 A	06-10-1992
			CA 2060242 A	01-08-1992
			DE 69215395 D	09-01-1997
			DE 69215395 T	22-05-1997
			EP 0497607 A	05-08-1992
			ES 2094285 T	16-01-1997
			JP 4343844 A	30-11-1992
			MX 9200389 A	01-08-1992
FR 2783412	A	24-03-2000	AU 5523999 A	10-04-2000
			WO 0016725 A	30-03-2000
US 4661099	A	28-04-1987	DE 3341555 A	30-05-1985
			AT 25999 T	15-04-1987
			AU 570744 B	24-03-1988
			AU 3546684 A	23-05-1985

INTERNATIONAL SEARCH REPORT

Information on patent family members

Internal Application No

PCT/GB 00/01415

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4661099 A		CA 1250190 A	21-02-1989
		DE 3462697 D	23-04-1987
		EP 0147588 A	10-07-1985
		ES 537614 D	01-01-1986
		ES 8603929 A	16-05-1986
		GR 80947 A	26-02-1985
		IL 73514 A	31-10-1989
		JP 1622491 C	25-10-1991
		JP 2042394 B	21-09-1990
		JP 60118783 A	26-06-1985
		KR 9310440 B	25-10-1993
		PT 79501 A	01-12-1984
WO 9742985 A	20-11-1997	SE 505000 C	09-06-1997
		CN 1193282 A	16-09-1998
		EP 0855921 A	05-08-1998
		JP 11509462 T	24-08-1999
		SE 9601853 A	09-06-1997
		US 6051747 A	18-04-2000
EP 0676457 A	11-10-1995	CA 2146286 A	07-10-1995
		DE 69505176 D	12-11-1998
		DE 69505176 T	10-06-1999
		US 5614586 A	25-03-1997
		US 5674275 A	07-10-1997

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.